

TECHNICAL DATASHEET

SAP No. 30007628 Article Description Q-E-1184g/m²-1270mm

Textile Structure 7007700 SAERTEX®

ARTICLE CONSTRUCTION (in accordance with EN 13473-1)

Layer	Construction	Areal weight	Tolerance	Material
4	0 °	295 g/m ²	+/- 5,0 %	E-glass 600 TEX
3	45 °	300 g/m ²	+/- 5,0 %	E-glass 300 TEX
2	90 °	283 g/m ²	+/- 5,0 %	E-glass 600 TEX
1	-45 °	300 g/m ²	+/- 5,0 %	E-glass 300 TEX
Stitching		6 g/m ²	+/- 1 g/m ²	PES [Polyester] 76 dtex

Fiber input can be determined individually

FURTHER CHARACTERISTICS

Gauge	5,0	Stitching pattern	tricot-warp	Width (nominal)	1270 mm
Stitch length	2,60 mm	Total tolerance	+/- 5,1 %	Total areal weight	1184 g/m ²

Labelling (Standard) Every roll is equipped with a label in the core. A further label is located outside on the foil or on the box.

Packaging (Standard) Every roll is wound on a cardboard core and wrapped in foil. Further packaging options can be determined individually.

Storage (recommendation) Keep in original packaging. Store in a dry environment. Avoid direct sunlight. Fabrics to be kept under processing conditions at least 24 hours prior to use to avoid problems with humidity and electrostatic charge.