

## TECHNICAL DATASHEET

SAP No. 30002930 Article Description Q-E-1233g/m<sup>2</sup>-1270mm LEO

Textile Structure 7002708 LEO<sup>®</sup>

### ARTICLE CONSTRUCTION (in accordance with EN 13473-1)

Layer	Construction	Areal weight	Tolerance	Material
4	0 °	319 g/m <sup>2</sup>	+/- 5,0 %	E-glass 900 TEX
3	45 °	300 g/m <sup>2</sup>	+/- 5,0 %	E-glass 300 TEX
2	90 °	307 g/m <sup>2</sup>	+/- 5,0 %	E-glass 600 TEX
1	-45 °	300 g/m <sup>2</sup>	+/- 5,0 %	E-glass 300 TEX
Stitching		7 g/m <sup>2</sup>	+/- 2 g/m <sup>2</sup>	Polyester (PES) 83 dtex

### FURTHER CHARACTERISTICS

Gauge	5,0	Stitching pattern	tricot	Width (nominal)	1.270 mm
Stitch length	2,60 mm	Total tolerance	+/- 5,1 %	Total areal weight	1233 g/m <sup>2</sup>

Labelling (Standard) Every roll is equipped with a label in the core. A further label is located outside on the foil or on the box.

Packaging (Standard) Every roll is wound on a cardboard core and wrapped in foil. Further packaging options can be determined individually.

Storage With original packaging: No moisture recommendation and direct sunlight. To avoid problems with humidity and electrostatic charge, fabrics to be conditioned 24 hours prior to processing, independent of storage conditions.