

TECHNICAL DATASHEET

SAP No. 30008289 Article Description SAERcore LEO 750/PP24/750 1747g/m²1250mm
Textile Structure 7008121 SAERcore[®]

ARTICLE CONSTRUCTION (in accordance with EN 13473-1)

Layer	Construction	Areal weight	Tolerance	Material
3	CSM	750 g/m ²	+/- 10,0 %	E-glass
2	Core	240 g/m ²	+/- 10,0 %	PP FR
1	CSM	750 g/m ²	+/- 10,0 %	E-glass
Stitching		7 g/m ²	+/- 2 g/m ²	Polyamide 6.6 122 dtex

Fiber input can be determined individually

FURTHER CHARACTERISTICS

Gauge	3,5	Stitching pattern	tricot	Width (nominal)	1250 mm
Stitch length	4,00 mm	Total tolerance	+/- 10,1 %	Total areal weight	1747 g/m ²

Tracer yarn¹ 1 PC black

¹Position can be determined individually

Labelling (Standard) Every roll is equipped with a label in the core. A further label is located outside on the foil or on the box.

Packaging (Standard) Every roll is wound on a cardboard core and wrapped in foil. Further packaging options can be determined individually.

Storage With original packaging: No moisture recommendation and direct sunlight. To avoid problems with humidity and electrostatic charge, fabrics to be conditioned 24 hours prior to processing, independent of storage conditions.

Important advice The Z side of the stitching line should be place preferably on the cosmetic face to obtain the best surface finish.