

TECHNICAL DATASHEET

SAP No. 30001266 Article Description X-C-408g/m²-1270mm LEO

Textile Structure 7002102 LEO[®]

ARTICLE CONSTRUCTION (in accordance with EN 13473-1)

| Layer | Construction | Areal weight | Tolerance | Material |
|-----------|--------------|----------------------|------------------------|-------------------------|
| 3 | -45 ° | 200 g/m ² | +/- 5,0 % | TORAY T700SC F0E 12K |
| 2 | 0 ° | 1 g/m ² | +/- 5,0 % | E-glass 34 TEX |
| 1 | 45 ° | 200 g/m ² | +/- 5,0 % | TORAY T700SC F0E 12K |
| Stitching | | 7 g/m ² | +/- 2 g/m ² | Polyester (PES) 83 dtex |

FURTHER CHARACTERISTICS

| | | | | | |
|---------------|---------|-------------------|-----------|--------------------|----------------------|
| Gauge | 5,0 | Stitching pattern | tricot | Width (nominal) | 1.270 mm |
| Stitch length | 2,60 mm | Total tolerance | +/- 5,4 % | Total areal weight | 408 g/m ² |

Labelling (Standard) Every roll is equipped with a label in the core. A further label is located outside on the foil or on the box.

Packaging (Standard) Every roll is wound on a cardboard core and wrapped in foil. Further packaging options can be determined individually.

Storage With original packaging: No moisture recommendation and direct sunlight. To avoid problems with humidity and electrostatic charge, fabrics to be conditioned 24 hours prior to processing, independent of storage conditions.