

TECHNICAL DATASHEET

SAP No. 30000447 Article Description X-E-813g/m²-1270mm LEO

Textile Structure 7000216 LEO®

| ARTICLE CONSTRUCTION (in accordance with EN 13473-1) | | | | | | | | |
|--|--------------|--------------|------------|-------------------------|--|--|--|--|
| Layer | Construction | Areal weight | Tolerance | Material | | | | |
| 4 | 45 ° | 401 g/m² | +/- 5,0 % | E-glass 600 TEX | | | | |
| 3 | 90 ° | 3 g/m² | +/- 5,0 % | E-glass 68 TEX | | | | |
| 2 | 0 ° | 1 g/m² | +/- 5,0 % | E-glass 68 TEX | | | | |
| 1 | -45 ° | 401 g/m² | +/- 5,0 % | E-glass 600 TEX | | | | |
| Stitching | | 7 g/m² | +/- 2 g/m² | Polyester (PES) 83 dtex | | | | |

| FURTHER CHARACTERISTICS | | | | | | | | | |
|-------------------------|---------|-------------------|-----------|--------------------|----------|--|--|--|--|
| Gauge | 5,0 | Stitching pattern | warp | Width (nominal) | 1.270 mm | | | | |
| Stitch length | 2,60 mm | Total tolerance | +/- 5,2 % | Total areal weight | 813 g/m² | | | | |

Labelling (Standard) Every roll is equipped with a label in the core. A further label is located outside on

the foil or on the box.

Packaging (Standard) Every roll is wound on a cardboard core and wrapped in foil. Further packaging

options can be determined individually.

Storage With original packaging: No moisture recommendation and direct sunlight.

To avoid problems with humidity and electrostatic charge, fabrics to be conditioned 24 hours prior to processing, independent of storage conditions.